


AQUARELLE FLOOR

Datasheet

Classification	Norm Test	Tarkett Value
Product type	ISO 10582	Heterogeneous poly(vinyl chloride) floor coverings
Commercial classification	ISO 10874	31 Moderate
Binder content	ISO 10582	Type I
Technical Characteristics	Norm Test	Tarkett Value
Wear layer thickness	EN ISO 24340	0,35 mm
Total thickness	EN ISO 24346	1,50 mm
Total weight	EN ISO 23997	2400 g/m²
Surface treatment		Top Clean
Installation method		Glue-Down
Performance for CE Marking	Norm Test	Tarkett Value
Declaration of Performance #	EN 14041	0131-0043-DoP-2013-07
Reaction to fire	EN ISO 13501-1	Bfl-s1
Static Electrical Propensity	EN 1815	Antistatic (≤ 2 kV)
Thermal resistance	EN ISO 10456	0,01 m²·K/W
Slip resistance (EN 13893)	EN 13893	Class DS ($\mu \geq 0,30$)
Technical Performance	Norm Test	Tarkett Value
Residual indentation	EN ISO 24343-1	$\leq 0,10$ mm
Dimensional stability	EN ISO 23999	Average Measured Value : ≤ 0.40 %
Curl resultant to heat	EN ISO 23999	$\leq 8 $ mm
Light fastness	EN ISO 105-B02	≥ 6
Chemical resistance	EN ISO 26987	Not affected
Underfloor heating		Suitable (subfloor temperature maximum 27°C)
Sustainability performances	Norm Test	Tarkett Value
Recyclability through ReStart®		Recyclable
Recycled content		11,5 %
Carbon Footprint (Cradle-to-Gate, EPD Modules A1-A3)		5,67 kg CO ₂ eq /m²
Total VOC Emissions (after 28 days)	EN 16516	Platinum (≤ 10 µg/m³)
Formaldehyde emission	EN 717-1	E1
Dimensions and designs		
Roll		Roll 2 x 25 m
Number of designs available		18



The above information is subject to modification for the benefit of further improvement (05/10/2025). According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website <https://www.tarkett.com>. Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.