

# ICONIK 200

## Datasheet

Classification	Norm	Tarkett Value
Product type	EN ISO 26986	Expanded (cushioned) poly(vinyl chloride) floor covering
Domestic classification	EN ISO 10874	21 Moderate/Light
Binder content	ISO 11638	Type I
Technical Characteristics	Norm	Tarkett Value
Total thickness	ISO 24346	2 mm
Wear layer thickness	ISO 24340	0,15 mm
Total weight	ISO 23997	1380 g/m <sup>2</sup>
Performance for CE Marking	Norm	Tarkett Value
Declaration of Performance #	EN 14041	0007-0012-DOP-2022-03
Reaction to fire	EN 13501-1	Cfl-s1
Slip resistance	EN 13893	Class DS ( $\mu \geq 0,30$ )
Slip resistance	DIN 51130	R10
Static Electrical Propensity	EN 1815	Antistatic ( $\leq 2$ kV)
Thermal resistance	ISO 10456	0,030 m <sup>2</sup> •K/W
Technical Performance	Norm	Tarkett Value
Residual indentation	EN ISO 24343-1	$\leq 0,25$ mm
Impact sound reduction - $\Delta L_w$	EN ISO 717-2	17 dB
Colour fastness to light	ISO 105-B02	$\geq 6$
Chemical resistance	ISO 26987	Not affected
Underfloor heating		Suitable (subfloor temperature maximum 27°C)
Dimensional stability	EN ISO 23999	Average measured value : $\leq 0.15$ %
Sustainability performances	Norm	Tarkett Value
Recyclability through ReStart®		Recyclable
Recycled content		16 %
Carbon Footprint (Cradle-to-Gate, EPD Modules A1-A3)		5,01 kg CO <sub>2</sub> eq /m <sup>2</sup>
Total VOC Emissions	EN 16516	Gold ( $\leq 100$ $\mu\text{g} / \text{m}^3$ )
BREEAM rating		A+
Formaldehyde emission class		E1
Dimensions and designs		
Roll		Roll 2 x 25 m Roll 3 x 25 m Roll 4 x 25 m
Number of designs available		8



The above information is subject to modification for the benefit of further improvement (05/09/2023). According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website <https://www.tarkett.com>. Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.