

iQ GRANIT ACOUSTIC

Datasheet

Technical Characteristics & Technical Performance	Norm	Tarkett Value	Requirement
Product type	EN 651	Heterogeneous poly(vinyl chloride) flooring on foam (ISO 11638)	
Characteristics & Technical Performance	Norm	Tarkett Value	Requirement
Country of origin		Sweden	
Surface treatment		New iQ PUR	
Total thickness	ISO 24346	3.5 mm	
Technical Characteristics & Technical Performance	Norm	Tarkett Value	Requirement
Commercial classification	ISO 10874	34 Very Heavy	
Industrial classification	ISO 10874	42 General	
Characteristics & Technical Performance	Norm	Tarkett Value	Requirement
Wear layer thickness	ISO 24340	2 mm	0.65 mm
Total weight	ISO 23997	3.81 kg/m ²	
Binder content	ISO 10582	Type II	
Installation method		Glue-Down	
Format Type		Roll	
Performance for CE Marking	Norm	Tarkett Value	Requirement
Static Electrical Propensity	EN 1815	Antistatic (≤ 2 kV)	
Declaration of Performance #	EN 14041	0019-0040-DoP-2013-07	
Reaction to fire on woodchip substrate	EN 13501-1	Bfl-s1	
Technical Performance	Norm	Tarkett Value	Requirement
Furniture leg effect	EN 424	No damage	
Residual indentation		≤ 0.20 mm Best measured value: 0,09 mm	
Impact sound reduction - ΔL_w	EN ISO 717-2	15 dB	15 dB
Castor chair effect	ISO 4918	Suitable	
Chemical resistance ISO	ISO 26987	Excellent Resistance	
Underfloor heating		YES_27	
Colour fastness to light	ISO 105-B02	≥ 7	
Sustainability, Environment & Indoor Air Quality	Norm	Tarkett Value	Requirement
ReStart® Ready		Yes	
Phthalate - free		Yes	
Tarkett Indoor Air Quality (TVOC after 28 days)	EN 16516	Platinum (≤ 10 $\mu\text{g} / \text{m}^3$)	
Dimensions and designs			
Roll		Roll 1,95 x 23 m	
Number of designs available		24	



The above information is subject to modification for the benefit of further improvement (05/05/2022). Tarkett reserves the right to amend this specification without giving prior notice. For the latest versions of the technical specifications, visit professional.tarkett.com