

# Standard Plus (2.0 mm)

## Datasheet

| Classification                                       | Norm                           | Tarkett Value                                |
|------------------------------------------------------|--------------------------------|----------------------------------------------|
| Product type                                         | ISO 10581                      | Homogeneous vinyl floor covering             |
| Binder content                                       | ISO 10581                      | Type II                                      |
| Commercial classification                            | ISO 10874                      | 34 Very Heavy                                |
| Industrial classification                            | ISO 10874                      | 43 Heavy                                     |
| Technical Characteristics                            | Norm                           | Tarkett Value                                |
| Surface treatment                                    |                                | PUR                                          |
| Total thickness                                      | ISO 24346                      | 2 mm                                         |
| Wear layer thickness                                 | ISO 24340                      | 2 mm                                         |
| Total weight                                         | ISO 23997                      | 3300 g/m <sup>2</sup>                        |
| Performance for CE Marking                           | Norm                           | Tarkett Value                                |
| Declaration of Performance #                         | EN 14041                       | 0019-0025-DoP-2013-07                        |
| Reaction to fire                                     | EN 13501-1                     | Bfl-s1                                       |
| Reaction to fire                                     | EN ISO 9239-1                  | ≥ 8 kW/m <sup>2</sup>                        |
| Reaction to fire - EN ISO 11925-2                    | EN ISO 11925-2                 | Pass                                         |
| Static Electrical Propensity                         | EN 1815                        | Antistatic (≤ 2 kV)                          |
| Thermal resistance                                   | EN 12667                       | ~0,010 m <sup>2</sup> •K/W                   |
| Slip resistance                                      | EN 13893                       | Class DS (μ ≥ 0,30)                          |
| Technical Performance                                | Norm                           | Tarkett Value                                |
| Marine Equipment                                     | IMO 2010 FTP Code part 2 and 5 | Approved                                     |
| Residual indentation                                 | EN ISO 24343-1                 | ≤ 0,10 mm<br>Best measured value: 0,04 mm    |
| Slip resistance                                      | DIN 51130                      | R9                                           |
| Slip Resistance                                      | BS 7976-2                      | Low risk of slip                             |
| Curl resultant to heat                               | EN ISO 23999                   | ≤ 8 mm for rolls                             |
| Castor chair                                         | ISO 4918                       | Suitable                                     |
| Light fastness                                       | ISO 105-B02                    | ≥ 6                                          |
| Dimensional stability                                | EN ISO 23999                   | Average Measured Value : ≤ 0.40 % for rolls  |
| Chemical resistance                                  | ISO 26987                      | Good resistance                              |
| Bacteria Resistance                                  | ISO 846 Part C                 | Does not promote growth                      |
| Underfloor heating                                   |                                | Suitable (subfloor temperature maximum 27°C) |
| Seam Strength Average Value                          | EN 684                         | ≥ 400 N/50mm                                 |
| Sustainability performances                          | Norm                           | Tarkett Value                                |
| Recyclability through ReStart®                       |                                | Recyclable                                   |
| Recycled content                                     |                                | 25,5 %                                       |
| Carbon Footprint (Cradle-to-Gate, EPD Modules A1-A3) |                                | 5,69 kg CO <sub>2</sub> eq /m <sup>2</sup>   |
| Total VOC Emissions (after 28 days)                  | EN 16516                       | Platinum (≤ 10 µg/m <sup>3</sup> )           |
| Formaldehyde emission                                |                                | E1                                           |
| Dimensions and designs                               |                                |                                              |
| Roll                                                 |                                | Roll 2 x 23 m                                |
| Number of designs available                          |                                | 30                                           |



The above information is subject to modification for the benefit of further improvement (27/06/2024). According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website <https://www.tarkett.com>. Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.