

Safetred Spec

Datasheet

Classification	Norm	Tarkett Value
Product type	EN 13845	Polyvinyl chloride floor coverings with particle based enhanced slip resistance
Commercial classification	ISO 10874	34 Very Heavy
Industrial classification	ISO 10874	43 Heavy
Technical Characteristics	Norm	Tarkett Value
Total thickness	ISO 24346	2 mm
Total weight	ISO 23997	3410 g/m ²
Surface treatment		Safety Clean XP
Binder content	ISO 10582	Type I
Performance for CE Marking	Norm	Tarkett Value
Declaration of Performance #		0170-0003-DoP-2020-10
Reaction to fire	AS/ISO 9239.1	Critical radiant flux 8.0kW/m ² Smoke 261%.min
Static Electrical Propensity	EN 1815	Antistatic (≤ 2 kV)
Electrical resistance (vertical)	EN 1081	Static dissipative (≤ 1x10 ⁹ Ω)
Thermal resistance	ISO 10456	0,010 m ² ·K/W
Technical Performance	Norm	Tarkett Value
Residual indentation	EN ISO 24343-1	Required value: ≤ 0,10 mm
Abrasion particle loss	EN 13845 Annex D	≤ 10%
Dimensional stability	EN ISO 23999	Average Measured Value : ≤ 0.40 %
Slip resistance	DIN 51130	R10
	AS 4586	P3
Surface Roughness Rz		> 20µm
Castor chair	ISO 4918	No damage
Furniture leg	ISO 16581	No damage
Colour fastness to light	ISO 105-B02	≥ 7
Impact sound reduction - ΔLw	EN ISO 717-2	4 dB
Underfloor heating	BS 8203	Suitable (subfloor temperature maximum 27°C)
Curl resultant to heat	EN ISO 23999	≤ 2 mm
Chemical resistance	ISO 26987	Good resistance
Sustainability performances	Norm	Tarkett Value
Recyclability through ReStart®		Recyclable
Carbon Footprint (Cradle-to-Gate, EPD Modules A1-A3)		9,15 kg CO ₂ eq /m ²
Total VOC Emissions	EN 16516	Platinum (≤ 10 µg/m ³)
Recycled content		42%
GreenTag		Level A
HealthRATE		Platinum
Dimensions and designs		
Roll		Roll 2 x 20 m
Number of designs available		9



The above information is subject to modification for the benefit of further improvement (13/2/2023). According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website <https://www.tarkett.com>. Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.

Tarkett Australia
 Suite 1, Level 3, 3 Columbia Court, Baulkham Hills NSW 2153
 (02) 8853 1200
customerservice@tarkett.com
www.tarkett.com.au

