

iD Elegance 55

iD Elegance 55 Max

LUXURY VINYL TILES

TECHNICAL DATA	STANDARD	iD ELEGANCE 55	iD ELEGANCE MAX 55
CLASSIFICATION			
Classification	EN ISO 10582	Heterogeneous PVC floor covering	
	EN ISO 10874	Domestic: 23 - Commercial: 33	
Wear layer binder content	EN ISO 10582	Type I	
TECHNICAL CHARACTERISTICS			
Total thickness	EN ISO 24346	2.50 mm	3.00 mm
Total weight	EN ISO 23997	4360 g/m²	5500 g/m²
Wear layer thickness	EN ISO 24340	0.55 mm	
Bevelled edges		No	
Surface treatment (PUR)		Yes - TopClean	
Form of delivery	EN ISO 24342		
	Planks 229 x 1219 mm	10 planks/box = 2.79m² 72 boxes/pallet = 200.88m²	8 planks/box = 2.23m² 72 boxes/pallet = 160.56m²
	Tiles 610x 305 mm	14 tiles/box = 2.60m² 64 boxes/pallet = 166.40m²	12 tiles/box = 2.23m² 64 boxes/pallet = 142.72m²
	Tiles 457x 457 mm	10 tiles/box = 2.09m² 80 boxes/pallet = 167.20m²	8 tiles/box = 1.67m² 80 boxes/pallet = 133.76m²
PERFORMANCES FOR CE MARKING REQUIREMENTS (EN 14041)			
Reaction to fire	EN 13501-1	Bfl-s1 glued over A2fl or A1fl substrate (concrete)	
Electrostatic properties	EN 1815	≤ 2.0 kV on concrete	
	EN 1081	R1 > 10 ¹⁰ Ω	
Thermal resistance	EN ISO 10456	0.03 m² K/W	
Slip resistance	EN 13893	μ ≥ 0.3	
TECHNICAL PERFORMANCES			
Residual indentation	EN ISO 24343-1	Required value: ≤ 0.10 mm Average measured value: 0.03 mm	
Impact sound reduction	NF EN ISO 717 / 2	ΔLw 4 dB	
Slip resistance	DIN 51130	R9	
Furniture leg	EN 424	No damage	
Castor chair	EN ISO 4918	No damage	
Curl resultant to heat	EN ISO 23999	≤ 2 mm	
Light fastness	EN ISO 105-B02	≥ 6	
Dimensional stability	EN ISO 23999	≤ 0.25%	
Chemical resistance	EN ISO 26987	Good resistance	
Underfloor heating		Suitable – max. 27°C	
ENVIRONMENTAL PERFORMANCES			
Total VOC emissions	ISO 16000-9	≤ 100 µg/m³ (after 28 days)	
COLOURS			
Wood:37 / Stone:12 / Texture:19			

The above information is subject to modification for the benefit of further improvement (04/2025). For the latest information, please visit our website: www.Tarkett-Asia.com

Tarkett's instructions regarding installation, cleaning and maintenance should be observed.

