



Arcade

Specification according to EN 1307

Type of manufacture	ISO 2424		Tufted 1/8 “						
Aspect	ISO 2424		Cut pile						
Dye method			Piece dyed continuous						
Dimension	EN ISO 24342	cm x cm	50 x 50 / 19,68” x 19,68” (16 tiles per box)						
Primary backing	ISO 2424		Polyester fleece						
Secondary backing	ISO 2424		ProBase - modified bitumen.						
Pile fibre composition	ISO 2424		BCF Polyamide 6.6						
Total thickness	ISO 1765	mm	10.5	inch	0.4				
Effective pile thickness	ISO 1766	mm	7.0	inch	0.28				
Total mass	ISO 8543	g/m²	4700	oz/yd²	138.7				
Total pile mass	ISO 2424	g/m²	1540	oz/yd²	45.5				
Effective pile mass	ISO 8543	g/m²	1200	oz/yd²	35.4				
Pile density	ISO 8543	g/cm³	0.171	lb/in³	0.0062				
Number of tufts	ISO 1763	/dm²	1070	/yd²	89463				
Stroll test	ISO 6356	kV	≤ 2,0						
Vertical resistance	ISO 10965	Ohm	-						
Horizontal resistance	ISO 10965	Ohm	-						
Use classification	EN 1307		32 Commercial - general use						
Luxury rating	EN 1307		LC 5						
Dimensional stability	EN 986	%	≤ 0,2						
Impact sound reduction ΔL _w	ISO 10140	dB	28						
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000	
		α _s	0.01	0.05	0.10	0.30	0.50	0.70	
Noise reduction	ISO 354	α _w	0.20						
Thermal resistance	ISO 8302	m².K/W	0.125						
Flammability	EN 13501-1		Cfl - s1 (loose laid tested)						
Prodis - GUT	www.pro-dis.info		F7DA50EA						



DESSO flooring products are to be installed in full accordance with Tarkett's installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. DESSO flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com

FN-20240528