

Axminster in-Stock (Marine)

Specification according to EN 1307

Type of manufacture	ISO 2424		Woven - Axminster					
Aspect	ISO 2424		Cut pile					
Dye method			Hank dyed					
Width		cm	400		ft	13.1		
Primary backing	ISO 2424		Polypropylene weft / Polyester-based warp					
Secondary backing	ISO 2424		Copolymer					
Pile fibre composition	ISO 2424		80% wool - 20% polyamide					
Total thickness	ISO 1765	mm	9.0		inch	0.4		
Effective pile thickness	ISO 1766	mm	7.0		inch	0.28		
Total mass	ISO 8543	g/m²	1760		oz/yd²	51.9		
Total pile mass	ISO 2424	g/m²	1355		oz/yd²	40.0		
Effective pile mass	ISO 8543	g/m²	920		oz/yd²	27.2		
Pile density	ISO 8543	g/cm³	0.131		lb/in³	0.0047		
Number of tufts	ISO 1763	/dm²	870		/yd²	72741		
Stroll test	ISO 6356	kV	-					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307		33 Commercial - heavy use					
Luxury rating	EN 1307		LC 4					
Impact sound reduction ΔL _w	ISO 10140	dB	32					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α _s	0.01	0.08	0.12	0.25	0.49	0.62
Noise reduction	ISO 354	α _w	0.20					
Thermal resistance	ISO 8302	m².K/W	0.155					
Flammability	EN 13501-1		-					
Prodis - GUT	www.pro-dis.info		-					

Manufactured by:

EN 14041

Tarkett NV
Robert Ramlotstraat 89
B - 9200 Dendermonde



Tarkett's flooring products are to be installed in full accordance with DESSO installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. Tarkett's flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com

EN-20191004