



Axminster Sculpt

Preliminary specification according to EN 1307

Type of manufacture	ISO 2424		Woven - Axminster (Decor B - 9 row, 3ply)					
Aspect	ISO 2424		Structured cut pile					
Dye method			Hank dyed					
Width		cm	400		ft	13.1		
Primary backing	ISO 2424		Polypropylene weft / Polyester-based warp					
Secondary backing	ISO 2424		Copolymer					
Pile fibre composition	ISO 2424		80% wool - 20% polyamide					
Total thickness	ISO 1765	mm	9.5		inch	0.4		
Effective pile thickness	ISO 1766	mm	7.0		inch	0.28		
Total mass	ISO 8543	g/m²	1860		oz/yd²	54.9		
Total pile mass	ISO 2424	g/m²	1490		oz/yd²	44.0		
Effective pile mass	ISO 8543	g/m²	1040		oz/yd²	30.7		
Pile density	ISO 8543	g/cm³	0.149		lb/in³	0.0054		
Number of tufts	ISO 1763	/dm²	975		/yd²	81520		
Stroll test	ISO 6356	kV						
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307		33 Commercial - heavy use					
Luxury rating	EN 1307		LC 4					
Impact sound reduction ΔL _w	ISO 10140	dB	33					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α _s	0.00	0.04	0.15	0.28	0.48	0.63
Noise reduction	ISO 354	α _w	0.25					
Thermal resistance	ISO 8302	m².K/W	0.154					
Flammability	EN 13501-1		Cfl - s1 (glued tested)					
Prodis - GUT	www.pro-dis.info							



DESSO flooring products are to be installed in full accordance with Tarkett's installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. DESSO flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com

EN-20240703