




Conga


Specification according to EN 1307


Type of manufacture	ISO 2424	Tufted 1/10 "						
Aspect	ISO 2424	Loop pile						
Dye method		Piece dyed						
Width	cm	400	ft	13.1				
Primary backing	ISO 2424	Polypropylene woven + fleece						
Secondary backing	ISO 2424	Polypropylene woven - Sandwich Backing						
Pile fibre composition	ISO 2424	BCF Polyamide 6						
Total thickness	ISO 1765	mm	6.0	inch	0.2			
Effective pile thickness	ISO 1766	mm	3.0	inch	0.12			
Total mass	ISO 8543	g/m ²	1800	oz/yd ²	53.1			
Total pile mass	ISO 2424	g/m ²	620	oz/yd ²	18.3			
Effective pile mass	ISO 8543	g/m ²	400	oz/yd ²	11.8			
Pile density	ISO 8543	g/cm ³	0.133	lb/in ³	0.0048			
Number of tufts	ISO 1763	/dm ²	2050	/yd ²	171401			
Stroll test	ISO 6356	kV	≤ 2,0					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307	23 Domestic - heavy use						
Luxury rating	EN 1307	LC 2						
Impact sound reduction ΔL _w	ISO 10140	dB	-					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α _s	-	-	-	-	-	-
Noise reduction	ISO 354	α _w	-					
Thermal resistance	ISO 8302	m ² .K/W	0.090					
Flammability	EN 13501-1	Cfl - s1 (glued tested)						
Prodis - GUT	www.pro-dis.info	B311D1A0						


 Manufactured by:
 Tarkett BV
 Parallelweg 14
 NL - 5051 HG Goirle

EN 14041
 0493-CPR-0003





Tarkett's flooring products are to be installed in full accordance with DESSO installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. Tarkett's flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com

EN-20190514