


Excellent

Specification according to EN 1307

Type of manufacture	ISO 2424		Tufted 1/8 "					
Aspect	ISO 2424		Cut pile					
Dye method			Stock dyed					
Width		cm	400 - 500	ft	13,1 - 16,6			
Primary backing	ISO 2424		Polypropylene woven + fleece					
Secondary backing	ISO 2424		Polypropylene woven					
Pile fibre composition	ISO 2424		80% wool - 10% polyamide - 10% polyester					
Total thickness	ISO 1765	mm	11.1	inch	0.4			
Effective pile thickness	ISO 1766	mm	8.1	inch	0.32			
Total mass	ISO 8543	g/m²	2580	oz/yd²	76.1			
Total pile mass	ISO 2424	g/m²	1350	oz/yd²	39.8			
Effective pile mass	ISO 8543	g/m²	1095	oz/yd²	32.3			
Pile density	ISO 8543	g/cm³	0.135	lb/in³	0.0049			
Number of tufts	ISO 1763	/dm²	1228	/yd²	102673			
Stroll test	ISO 6356	kV	≤ 2,0					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307		23 Domestic - heavy use (tested on carpet underlay)					
Luxury rating	EN 1307		LC 5					
Impact sound reduction ΔL _w	ISO 10140	dB	30					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α _s	0.01	0.03	0.15	0.35	0.58	0.65
Noise reduction	ISO 354	α _w	0.25					
Thermal resistance	ISO 8302	m².K/W	-					
Flammability	EN 13501-1		Cfl - s1 (glued tested)					
Prodis - GUT	www.pro-dis.info		DF93A296					



Tarkett's flooring products are to be installed in full accordance with DESSO installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. Tarkett's flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com

EN-20190515