


Patterns

Preliminary specification according to EN 1307

Type of manufacture	ISO 2424		Tufted 1/10 “					
Aspect	ISO 2424		Structured loop pile					
Dye method			Solution dyed					
Width		cm	400		ft	13.1		
Primary backing	ISO 2424		Polyester fleece					
Secondary backing	ISO 2424		Felt backing 250g					
Pile fibre composition	ISO 2424		BCF Polyamide 6 ECONYL®**					
Total thickness	ISO 1765	mm	8.2		inch	0.3		
Effective pile thickness	ISO 1766	mm	3.7		inch	0.15		
Total mass	ISO 8543	g/m²	1890		oz/yd²	55.8		
Total pile mass	ISO 2424	g/m²	560		oz/yd²	16.5		
Effective pile mass	ISO 8543	g/m²	365		oz/yd²	10.8		
Pile density	ISO 8543	g/cm³	0.099		lb/in³	0.0036		
Number of tufts	ISO 1763	/dm²	2170		/yd²	181434		
Stroll test	ISO 6356	kV	≤ 2,0					
Vertical resistance	ISO 10965	Ohm	-					
Horizontal resistance	ISO 10965	Ohm	-					
Use classification	EN 1307		23 Domestic - heavy use					
Luxury rating	EN 1307		LC 1					
Impact sound reduction ΔL _w	ISO 10140	dB	30					
Sound absorption	ISO 354	Freq. Hz	125	250	500	1000	2000	4000
		α _s	0.00	0.02	0.18	0.44	0.60	0.63
Noise reduction	ISO 354	α _w	0.25					
Thermal resistance	ISO 8302	m².K/W	0.133					
Flammability	EN 13501-1		Cfl - s1 (glued tested)					
Prodis - GUT	www.pro-dis.info		BADAB84D					



DESSO flooring products are to be installed in full accordance with Tarkett's installation instructions and recognized trade standards. An effective, regular cleaning and maintenance program is vital for retaining a high appearance level. DESSO flooring products should only be used as floorcoverings. Note: Tarkett reserves the right to change this specification without prior notice; changes are subject to normal production tolerances. For the latest versions of the technical specifications, visit www.tarkett.com

EN-20240704