

STARFLOOR CLICK ULTIMATE 55

TECHNICAL DATA

CLASSIFICATION	STANDARD	STARFLOOR CLICK ULTIMATE 55
Classification	EN ISO 10582	Heterogeneous Compact Resilient Floorcovering
	EN ISO 10874	Domestic: 23 - Commercial: 33 - Industrial: 42
Wear layer binder content	EN ISO 10582	Type I
TECHNICAL CHARACTERISTICS		
Total thickness	EN ISO 24346	6.5 mm
Total weight	EN ISO 23997	11.3 kg/m ²
Wear layer thickness	EN ISO 24340	0.55 mm
Bevelled edges		Yes - 4 Bevels
Surface treatment (PUR)		Yes - PUR Ultimate
Form of delivery	EN ISO 24342 Planks	176 x 1213 mm = 6 planks/box = .28 m ² /box
	EN ISO 24342 Tiles	300 x 600 mm = 7 tiles/box = 1.26 m ² /box
PERFORMANCES FOR CE MARKING REQUIREMENTS (EN 14041)		
Declaration of Performance	EN 14041	0132-0070-DoP-2018-01
Reaction to fire	EN 13501-1	B _{fl} -s1
Electrostatic properties	EN 1815	≤ 2 kV
Thermal resistance	EN ISO 10456	0.05 m ² K/W
Slip resistance	EN 13893	μ ≥ 0.3
TECHNICAL PERFORMANCES		
Dimensional stability	EN ISO 23999	Average measured value 0.05% Required value ≤ 0.15%
Impact sound reduction	EN ISO 717-2	ΔL _w 19 dB
Reduction of in-room impact noise	EN ISO 31-074	Class C (L _{n,e,w} < 85 dB)
Slip resistance	DIN 51130	R9
Furniture leg	EN 424	No damage
Castor chair	ISO 4918 - EN 425	No damage
Curl resistant to heat	EN ISO 23999	≤ 1 mm
Light fastness	EN ISO 105-B02 (method 3a)	≥ 6
Residual indentation	EN ISO 24343-1	≤ 0.05 mm
Chemical resistance	EN ISO 26987	Very good
Underfloor heating		Suitable – max. 27°C
Peeling resistance	EN ISO 24345	≥ 50N / 50mm
ENVIRONMENTAL PERFORMANCES		
Total VOC emissions	ISO 16000-9	≤ 100 μg/m ³ (after 28 days)

The above information is subject to modification for the benefit of further improvement. (10/20).

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.



Produced under license from I4F
<https://i4f-patents.com>