

PURE 831

TECHNICAL DATA



SUPER LOW FORMALDEHYDE BOARD

F☆☆☆☆ according to JIS A 5905

Classification	Standards	PURE 831
Product Type	EN 13329	Laminate Floor Covering
Classification	EN 13329	Domestic: 23 Commercial: 31
HDF Core Board Density	EN 323	900 kg/m³
Technical characteristics		
Total thickness	EN 14041	8.0 mm
Bevelled edges	-	4V-bevel (removed on request)
Installation method	-	Uniclick
Form of delivery	EN 13329	Plank 192 x 1210 mm 9 pieces / box (2.091m²)
Technical performance		
Abrasion Resistance	EN 13329	AC3
Impact Resistance	EN 13329	IC2 for 31 st class
Stain Resistance	EN 13329	None
Scratch Resistance	ISO 4586	3.5
Thickness Swelling	ISO 24336	≤8%
Moisture Resistance	EN 322	5 – 8
Surface Soundness	EN 13329	1 N/mm²
Bending strength (MOR)	EN 310	35
Internal bond strength (IR)	EN 319	1.4
Formaldehyde Emissions	JIS A 5905 EN 14041	F☆☆☆☆ E0
Surface Smoothness	EN 13329	Fw Concave = 0.30 Fw Convex = 0.15 Fl Concave = 0.50 Fl Convex = 1.00
Bacteria Resistance	ISO 22196	Antibacterial Activity

The above information is subject to modification for the benefit of further improvement (03/2023).
For the latest information, please visit our website: www.Tarkett-asia.com
Tarkett's instructions regarding installation, cleaning and maintenance should be observed.

