

Elektra SC

TECHNICAL DATA

Classification	Standards	Elektra SC
Classification	EN ISO 10581	Static conductive pressed homogeneous vinyl flooring
	EN ISO 10874	Commercial: 34 Industrial: 43
Wear Layer binder content	EN ISO 10581	Type I

Technical characteristics

Total thickness	EN ISO 24346	2.0 mm
Wear layer thickness	EN ISO 24340	2.0 mm
Total weight	EN ISO 23997	3000 g/m²
Surface treatment (PUR)	-	PUR Reinforced
Form of delivery	EN ISO 24341 Sheet (rolls)	Approx. 23 running meters x 200 cm Art. No. 21057 _ _ _ 3 digit colour number

Technical performance

Reaction to Fire	EN 13501-1	Bfl-s1
Residual Indentation	EN ISO 24343-1	Required value: ≤ 0.10 mm Best measured value*: 0.03 mm
Static electrical discharge	EN 1815	< 2 kV
Electrical insulation	VDE 0100, Part 600	Ri ≤ 5x10⁴ Ohms
Electrical resistance	EN 1081	Ri 5x10⁴ ≤ R ≤ 10⁶ Ohms
Slip resistance	DIN 51130	R9
Castor chair	ISO 4918	Suitable
Chemical resistance	ISO 26987	Good resistance
Bacteria resistance	ISO 846 Part C	Does not favour growth
Total VOC emissions	ISO 16000-9	≤ 10 µg/m³ (after 28 days)

The above information is subject to modification for the benefit of further improvement (03/2023).
For the latest information, please visit our website: www.Tarkett-asia.com
Tarkett's instructions regarding installation, cleaning and maintenance should be observed.

