

# Special PUR

## TECHNICAL DATA

| Classification            | Standards    | Special PUR                      |
|---------------------------|--------------|----------------------------------|
| Classification            | EN ISO 10581 | Homogeneous Vinyl Flooring       |
|                           | EN ISO 10874 | Commercial: 34<br>Industrial: 43 |
| Wear Layer binder content | EN ISO 10581 | Type II                          |

### Technical characteristics

|                         |                            |                                                                                   |
|-------------------------|----------------------------|-----------------------------------------------------------------------------------|
| Total thickness         | EN ISO 24346               | 2.0 mm                                                                            |
| Wear layer thickness    | EN ISO 24340               | 2.0 mm                                                                            |
| Total weight            | EN ISO 23997               | 3200 g/m²                                                                         |
| Surface treatment (PUR) | -                          | PUR                                                                               |
| Form of delivery        | EN ISO 24341 Sheet (rolls) | Approx. 23 running meters x 200 cm<br>Art. No. 306001 _ _ _ 3 digit colour number |

### Technical performance

|                         |                |                                                            |
|-------------------------|----------------|------------------------------------------------------------|
| Reaction to Fire        | EN 13501-1     | Bfl-s1                                                     |
| Residual Indentation    | EN ISO 24343-1 | Required value: ≤ 0.10 mm<br>Best measured value*: 0.04 mm |
| Slip resistance         | DIN 51130      | R9                                                         |
| Castor chair            | ISO 4918       | Suitable                                                   |
| Chemical resistance     | EN ISO 26987   | Good resistance                                            |
| Bacteria resistance     | ISO 846 Part C | Does not favour growth                                     |
| Total VOC emissions     | ISO 16000-9    | ≤ 10 µg/m³ (after 28 days)                                 |
| Dimensional Stability   | ISO 23999      | ≤ 0.40% (Rolls)                                            |
| Curl Resistance to heat | ISO 23999      | ≤ 8.00 mm                                                  |

The above information is subject to modification for the benefit of further improvement (03/2023).  
For the latest information, please visit our website: [www.Tarkett-asia.com](http://www.Tarkett-asia.com)  
Tarkett's instructions regarding installation, cleaning and maintenance should be observed.

