

# Vylon Plus PUR

## TECHNICAL DATA

| Classification            | Standards    | Vylon Plus PUR                   |
|---------------------------|--------------|----------------------------------|
| Classification            | EN ISO 10581 | Homogeneous Vinyl Flooring       |
|                           | EN ISO 10874 | Commercial: 34<br>Industrial: 43 |
| Wear Layer binder content | EN ISO 10581 | Type II                          |

### Technical characteristics

|                         |                            |                                                                                 |
|-------------------------|----------------------------|---------------------------------------------------------------------------------|
| Total thickness         | EN ISO 24346               | 2.0 mm                                                                          |
| Wear layer thickness    | EN ISO 24340               | 2.0 mm                                                                          |
| Total weight            | EN ISO 23997               | 3400 g/m²                                                                       |
| Surface treatment (PUR) | -                          | PUR                                                                             |
| Form of delivery        | EN ISO 24341 Sheet (rolls) | Approx. 20 running meters x 200 cm<br>Art. No. 3091 _ _ _ 3 digit colour number |

### Technical performance

|                      |                                   |                                                            |
|----------------------|-----------------------------------|------------------------------------------------------------|
| Reaction to Fire     | EN 13501-1                        | Bfl-s1                                                     |
| Marine Equipment     | IMO 2010 FTP Code<br>part 2 and 5 | Approved                                                   |
| Residual Indentation | EN ISO 24343-1                    | Required value: ≤ 0.10 mm<br>Best measured value*: 0.04 mm |
| Slip resistance      | DIN 51130                         | R9                                                         |
| Castor chair         | ISO 4918                          | Suitable                                                   |
| Chemical resistance  | EN ISO 26987                      | Good resistance                                            |
| Bacteria resistance  | ISO 846 Part C                    | Does not favour growth                                     |
| Total VOC emissions  | ISO 16000-9                       | ≤ 10 µg/m3 (after 28 days)                                 |

The above information is subject to modification for the benefit of further improvement (03/2023).  
For the latest information, please visit our website: [www.Tarkett-asia.com](http://www.Tarkett-asia.com)  
Tarkett's instructions regarding installation, cleaning and maintenance should be observed.

