

HETEROGENEOUS
ACOUSTIC VINYL

Tapiflex Excellence 65

Specification

Printed vinyl floorcovering on glass fibre non woven PVC foam backing
Polyurethane reinforcement.
Product standard: ISO 11638 / EN 651.

HETEROGENEOUS
COMPACT VINYL

Accent Excellence 80

Specification

Compact flexible vinyl floorcovering glass fibre reinforced, printed
Polyurethane reinforcement.
Product standard: ISO 10582 - EN 649.

CERTIFICATION & CLASSIFICATION	STANDARDS	Tapiflex Excellence 65 (Sheet)	Tapiflex Tiles 65	Accent Excellence 80 (Sheet)	Accent Unik (Sheet) Loose Lay Offer
Type of floorcovering	ISO 11638 / EN 651	Heterogeneous Acoustic Vinyl	Heterogeneous Acoustic Vinyl	-	-
Wear Layer Binder Content	ISO 10582	Type I	Type I	Heterogeneous Compact Vinyl Type I	Heterogeneous Compact Vinyl Type I
CE Certification	EN 14041	Yes	Yes	Yes	Yes
Classification	ISO 10874 - EN 685	34	34	34-43	32
TECHNICAL CHARACTERISTICS	STANDARDS	Tapiflex Excellence 65 (Sheet)	Tapiflex Tiles 65	Accent Excellence 80 (Sheet)	Accent Unik (Sheet) Loose Lay Offer
Surface Treatment		TopClean XP™	TopClean XP™	TopClean XP™	TopClean XP™
Total thickness	ISO 24346 - EN 428	3.05 mm	3.45 mm	2.00 mm	2.10 mm
Wear layer thickness	ISO 24340 - EN 429	0.65 mm	0.65 mm	0.80 mm	0.80 mm
Total weight	ISO 23997 - EN 430	2 850 g/m ²	3 410 g/m ²	3 100 g/m ²	3 140 g/m ²
Form of delivery	ISO 24344 - EN 426 Sheet (rolls) ISO 24342 - EN 427 Tiles (box)	approx. 23 running metres x 200 cm	- 50 x 50 cm - 20 tiles/box = 5.00 m ²	approx. 23 running metres x 200 cm	approx. 23 running metres x 200 cm
TECHNICAL PERFORMANCES	STANDARDS	Tapiflex Excellence 65 (Sheet)	Tapiflex Tiles 65	Accent Excellence 80 (Sheet)	Accent Unik (Sheet) Loose Lay Offer
Dimensional stability	EN 434	< 0.10%	< 0.10%	< 0.10%	< 0.10%
Reaction to fire	EN 13501-1	Bfl s1 on fibrement substrate A2fl Cfl s1 on woodchip substrate ≥ 19mm	Bfl s1 on fibrement substrate A2fl Cfl s1 on woodchip substrate ≥ 19mm	Bfl s1 on fibrement substrate A2fl Bfl s1 on woodchip substrate ≥ 19mm	Bfl s1 loose-laid over any A2fl or A1fl substrate with density ≥ 1200 kg/m ³ (on cement) Bfl s1 loose-laid over any derivative wood substrate with density ≥ 470 kg/m ³
Curl resultant to heat	ISO 23999 - EN 434	≤ 8 mm	≤ 2 mm	≤ 8 mm	≤ 8 mm
Residual indentation	ISO 24343-1 - EN 433	Required value: ≤ 0.20 mm Average measured value*: 0.10 mm Best measured value*: 0.08 mm	Required value: ≤ 0.20 mm Average measured value*: 0.12 mm Best measured value*: 0.10 mm	Required value: ≤ 0.10 mm Average measured value*: 0.03 mm	Required value: ≤ 0.10 mm Average measured value*: 0.03 mm
Impact sound reduction	EN ISO 140-8 EN ISO 717-2	ΔL _w 19 dB	ΔL _w 19 dB	ΔL _w 3 dB	ΔL _w 4 dB
Acoustical Improvement	NF S31-074	L _{n,e,w} < 65 dB - Class A	L _{n,e,w} < 65 dB - Class A	L _{n,e,w} < 85 dB - Class C	L _{n,e,w} < 75 dB - Class B
Castor wheel test	ISO 4918 - EN 425	No damage	No damage	No damage	No damage
Furniture leg	EN 424	No damage	No damage	No damage	No damage
Electrostatic properties	EN 1815 EN 1081	< 2 kV on concrete R1 > 10 ⁹ Ω	< 2 kV on concrete R1 > 10 ⁹ Ω	< 2 kV on concrete R1 > 10 ⁹ Ω	< 2 kV on concrete R1 > 10 ⁹ Ω
Total VOC emissions	AgBB/DIBt	≤ 10 µg/m ³ (after 28 days)	≤ 10 µg/m ³ (after 28 days)	≤ 10 µg/m ³ (after 28 days)	≤ 10 µg/m ³ (after 28 days)
Thermal resistance Underfloor heating	EN 12667	0.04 m ² K/W Suitable	0.04 m ² K/W Suitable	0.02 m ² K/W Suitable	0.02 m ² K/W Suitable
Light fastness	EN ISO 105-B02	≥ 6	≥ 6/8	≥ 6	≥ 6
Chemical resistance	ISO 26987 - EN 423	High resistance	High resistance	High resistance	High resistance
Hygiene		Does not contribute to infection spreading	Does not contribute to infection spreading	Does not contribute to infection spreading	Does not contribute to infection spreading
Slip resistance	DIN 51130 EN 13893	R9/R10 Woods ≥ 0,3	R9 ≥ 0,3	R9/R10 Woods ≥ 0,3	R9/R10 Woods ≥ 0,3
Colours		117	10	117	6

The above information is subject to modification for the benefit of further improvement. (10/14).

*For information - not binding

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

CUSTOMS TARIFF : 48205000000F

Our Sustainability tag explains the content of our products and how they contribute to our sustainability strategy and human well-being.



■ **WESTERN EUROPE:** Austria: Tarkett Holding GmbH, Niederlassung Wien – Tel. +43 1 47 88 062 ■ **Belgium:** Tarkett France Belux – Tel. +32 16 35 98 80 ■ **Denmark:** Tarkett A/S – Tel. +45 43 90 60 11 ■ **Finland:** Tarkett Oy – Tel. +358 9 4257 9000 ■ **France:** Tarkett SAS – Tel. +33 1 41 20 42 49 ■ **Germany:** Tarkett Holding GmbH, Bereich Objekt – Tel. +49 62 33 810 ■ **Greece:** Tarkett Monoprosopi Ltd – Tel. +30 210 6745 340 ■ **Italy:** Tarkett S.p.A. – Tel. +39 0744 7551 ■ **Luxembourg:** Tarkett GDL SA – Tel. +352 949 211 8804 ■ **Netherlands:** Tarkett Holding GmbH, Vestiging Nederland – Tel. +31 416 68 54 91 ■ **Norway:** Tarkett AS – Tel. +47 32 20 92 00 ■ **Portugal:** Tarkett SA – Tel. +351 21 427 64 20 ■ **Spain:** Tarkett Floors S.L. – Tel. +34 91 358 00 35 ■ **Sweden:** Tarkett Sverige AB – Tel. +46 771 25 19 00 ■ **Switzerland:** Tarkett Holding GmbH, Bereich Objekt Schweiz – Tel. +41 043 233 79 24 ■ **Turkey:** Tarkett Aspen – Tel. +90 212 213 65 80 ■ **United Kingdom:** Tarkett Ltd – Tel. +44 (0) 1622 854 040 ■ **EASTERN EUROPE:** **Baltic Countries:** Tarkett Baltics – Tel. +370 37 262 220 ■ **Czech Republic:** Tarkett France SAS, org. slozka – Tel. +420 271 001 602 ■ **Hungary:** Tarkett France SAS – Tel. +36 1 437 8150 ■ **Poland:** Tarkett Polska Sp. z o.o. – Tel. +48 22 639 31 68 ■ **Russian Federation:** ZAO Tarkett RUS – Tel. +7 495 775 3737 ■ **Slovakia:** Tarkett France SAS, org. zlozka – Tel. +421 248 291 317 ■ **South East Europe:** Tarkett Trade d.o.o. – Tel. +381 21 7557 649 (44) 569 12 21 ■ **Ukraine:** Tarkett UA – Tel. +38 (0) 44 569 12 21 ■ **ASIA AND OCEANIA:** Australia: Tarkett Australia Pty Ltd – Tel. +61 2 88 53 12 00 ■ **China:** Tarkett Floor Covering (Shanghai) Co. Ltd. – Tel. +86 (21) 60 95 68 38 ext 841 ■ **North East Asia:** Tarkett Hong Kong Limited – Tel. +852 2511 8716 ■ **India:** Tarkett France (India Branch) – Tel. +91 11 4352 4073 ■ **South East Asia:** Tarkett Flooring Singapore Pte. Ltd. – Tel. +65 6346 1585 ■ **AFRICA:** Tarkett International – Tel. +33 1 41 20 41 01 ■ **MIDDLE EAST:** Tarkett Middle East – Tel. +961 1 51 3363/4 ■ **Israel:** Tarkett International – Tel. +33 1 41 20 41 01 ■ **NORTH AMERICA:** USA: Tarkett Inc. – Tel. +1 713 869 5811 / Johnssonite – Tel. +1 440 543 8916 ■ **Canada:** Tarkett Inc. – Tel. +1 450 293 173 ■ **LATIN AMERICA:** Brazil: Tarkett – Tel. 55 12 3954 7108 ■ **Argentina - Chile - Uruguay:** Tarkett Latam Mercosur – Tel. 54 11 47 08 07 72 / 54 9 11 44 46 88 82 ■ **Colombia - Panama - Bolivia - Ecuador - Paraguay - Peru - Trinidad and Tobago:** Tarkett – Tel. 55 11 9 8410 9310 ■ **Mexico / Central America:** Tarkett Latam Mexico – Tel. 52 735 392-3948



www.professionals.tarkett.com