

	Standards	Tx Habitat
Classification		
Classification	ISO 10874 (EN 685)	Classes : 23 31
Characteristics		
Total thickness	EN ISO 24346	2,80 mm
Wear layer thickness	EN ISO 24340	0,35 mm
Total weight	EN ISO 23997	>2,5 kg/sqm
PU treatment	ISO 23997 (EN 430)	TopClean XP™
Performances Techniques		
Residual indentation	NF EN ISO 24343-1	Required value : 0,25 mm Average value measured* : 0,11 mm Best value measured* : 0,09 mm
Impact sound reduction	NF EN ISO 717/2	20 dB
Reaction to fire	NF EN 13501-1	C _f s1
Dimensions stability	NF EN ISO 23999	< 0,10 %
Furniture leg	NF EN 424	No damage
Castor chair	NF ISO 4918	No damage
Curl resultant to heat	NF EN ISO 23999	< 2,00 mm
Electrostatic properties	NF EN 1815	≤ 2 kV R1 > 10 ⁹ Ω
Chemical resistance	ISO 26987 (EN 423)	High resistance
Thermal resistance Underfloor heating	EN ISO 10456	0,04 m² K/W Suitable
Slip resistance ⁽¹⁾	DIN 51130	R10 ≥ 0,30
Slip resistance (coef.)	NF EN 13893	≥ 0,30
Light fastness	EN ISO 105-B02	> 6
Acoustical Improvement	NF S31-074	Class A
Colors		
		50
CE Marking		
DoP number		0132-0079-DoP-2019-11

* For information - not binding. (1) Please note that slip resistance may be impacted by usage and cleaning operations. According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website www.tarkett.com.
3m width cut - on demand.

Surface Treatment	Logistics Information	Warranty	Sustainability credentials
 	 Available in rolls : 2 m Rolls length : 25 ml  Available in rolls : 3 m Rolls length : 25 ml  Available in rolls : 4 m Rolls length : 25 ml		   