

iD INSPIRATION CLICK

TECHNICAL DATA

Certification & classification	Standards	iD Inspiration Click Solid 30	iD Inspiration Click Solid 55	iD Inspiration High Traffic Click 70
Type of floor covering	EN ISO 10582	Heterogeneous Compact Resilient Floorcovering	Heterogeneous Compact Resilient Floorcovering	Heterogeneous Compact Resilient Floorcovering
Classification	EN ISO 10874	Domestic: 23 Commercial: 31	Domestic: 23 Commercial: 33 Industrial: 42	Domestic: 23 Commercial: 34 Industrial: 43
Technical characteristics				
Total thickness	EN ISO 24346	5 mm	5 mm	5 mm
Wear layer thickness	EN ISO 24340	0,30 mm	0,55 mm	0,70 mm
Total weight	EN ISO 23997	8900 g/m ²	8850 g/m ²	8350 g/m ²
Wear layer binder content	EN ISO 10582	Type I	Type I	Type I
Dimensions	EN ISO 24342	Planks 19,70 x 121,70 cm, 7 planks/box = 1,61 m ² 24,70 x 149,70 cm, 5 planks/box = 1,79 m ²	Planks 19,70 x 121,70 cm, 7 planks/box = 1,61 m ² 24,70 x 149,70 cm, 5 planks/box = 1,79 m ²	Planks 19,70 x 121,70 cm, 7 planks/box = 1,61 m ² 24,70 x 149,70 cm, 5 planks/box = 1,79 m ²
		Tiles 33,03 x 60,70 cm, 9 tiles/box = 1,75 m ² 49,70 x 99,70 cm, 3 tiles/box = 1,46 m ²	Tiles 33,03 x 60,70 cm, 9 tiles/box = 1,75 m ² 49,70 x 99,70 cm, 3 tiles/box = 1,46 m ²	Tiles 33,03 x 60,70 cm, 9 tiles/box = 1,75 m ² 49,70 x 99,70 cm, 3 tiles/box = 1,46 m ²
Surface treatment (PUR)	-	Yes - Tektanium™	Yes - Tektanium™	Yes - Tektanium™
Beveled edges	-	Yes	Yes	Yes
Embossing in Register	-	Yes on Authentics references	Yes on Authentics references	Yes on Authentics references
Technical performances				
Dimensional stability standard value	EN ISO 23999	≤ 0,15 %	≤ 0,15 %	≤ 0,15 %
Dimensional stability average measured value	EN ISO 23999	≤ 0,10 %	≤ 0,10 %	≤ 0,10 %
Curl resultant to heat	EN ISO 24346	≤ 1 mm	≤ 1 mm	≤ 1 mm
Reaction to fire	EN ISO 24346	B _{fl} -s1 glued over concrete substrate	B _{fl} -s1 glued over concrete substrate	B _{fl} -s1 glued over concrete substrate
Residual indentation	EN ISO 24343-1	≤ 0,10 mm	≤ 0,10 mm	≤ 0,10 mm
Furniture leg	EN 424	No damage	No damage	No damage
Castor chair	ISO 4918 - EN 425	No damage	No damage	No damage
Impact sound reduction	EN ISO 717-2	ΔL _w = 5 dB	ΔL _w = 5 dB	ΔL _w = 5 dB
Reduction of in-room impact noise	NF S31-074	Class C (L _{w,ref} < 85 dB)	Class C (L _{w,ref} < 85 dB)	Class C (L _{w,ref} < 85 dB)
Thermal resistance	EN ISO 10456	0,05 m ² K/W	0,05 m ² K/W	0,05 m ² K/W
Light fastness	EN ISO 105-B02 (method 3a)	≥ 6	≥ 6	≥ 6
Chemical resistance	EN ISO 26987	Very good	Very good	Very good
Slip resistance	DIN 51130 EN 13893	R9 / R10 depending on embossing μ ≥ 0,30	R9 / R10 depending on embossing μ ≥ 0,30	R9 / R10 depending on embossing μ ≥ 0,30
Peeling resistance	-	≥ 50N / 50mm	≥ 50N / 50mm	≥ 50N / 50mm
Underfloor heating	-	Suitable - max. 27 °C	Suitable - max. 27 °C	Suitable - max. 27 °C
CE Marking				
DoP number	-	0197-0054-DoP-2021-02	0197-0011-DoP-2021-02	0197-0051-DoP-2021-02
Environmental tag				
VOC emission	ISO 16000-9	≤ 10 μg/m ³ after 28 days	≤ 10 μg/m ³ after 28 days	≤ 10 μg/m ³ after 28 days
Recycled content		35% production waste	35% production waste	35% production waste
Recyclable		Yes - installation and post-consumer waste	Yes - installation and post-consumer waste	Yes - installation and post-consumer waste
Plasticizer		Phthalate-free	Phthalate-free	Phthalate-free

CUSTOMS TARIFF : 4820 5000 00

The above information is subject to modification for the benefit of further improvement. (12/20).

According to the European Regulation N° 305/2011 for CE Marking, the Declarations of Performance are available on our website www.tarkett.com

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

